DuploCOLL® 50 U

Art. No. 11 00 78

Environmentally friendly transfer tape with dispersion acrylic adhesive

| Product construction | | | | |
|----------------------|--------------------|------------------|----------------|--|
| | Name | Colour | Thickness [mm] | |
| Liner | Silicone paper | yellow | approx. 0,08 | |
| Adhesive | Dispersion acrylic | | approx. 0,05 | |
| | | Total thickness: | approx. 0,13 | |

Product advantages

- The dispersion acrylic adhesive is distinguished by excellent initial adhesion (tack) and enters into the pores of materials on account of its soft consistency. The effective bonding surface therefore is increased by a multiple.
- Resistant to ageing and UV-radiation
- For foam lamination at room temperature only a slight laminating pressure is required to achieve perfect bonding.

Main application fields

- Making all kinds of foam self-adhesive
- Bonding of bituminous materials
- Mounting of rear boot linings (felt, carpet) in the automotive industry

| Product features | | Applicability on | |
|---|---------------------------------------|---|--|
| Initial adhesion Final adhesion Dimensional stability Adhesion on even surfaces Adhesion on rough surfaces Ageing resistance Weathering resistance Chemical resistance Resistance to plasticizers | • • • • • • • • • • • • • • • • • • • | Foam Rubber Fabric Glass/Ceramics Wood High energy plastics: PVC, PC, ABS, Low energy plastics: PE, PP, Metal Paper/Cardboard | |
| ● ● very suitable ● ○ suitable | ● ○ ○ suitable with reductions | ○ ○ ○ not suitable | |



DuploCOLL® 50 U

Art. No. 11 00 78

Environmentally friendly transfer tape with dispersion acrylic adhesive

| Specific technical data* | |
|--|---|
| Temperature range Temperature range under stress | -40 °C to +120 °C -40 °C to +80 °C** |
| Peel strength in accordance with DIN EN 1939 after 24 hours storage at room temperature on PVC foam Polyether foam Polyurethane foam Polyethylene foam Rubber Aluminium anodized | 9 N/25 mm 7 N/25 mm 8 N/25 mm 6 N/25 mm 5 N/25 mm 23 N/25 mm |
| Resistance to plasticizers: Peel strength in accordance with DIN EN 1939 after 7 days storage at 70 °C on Polyether foam Polyurethane foam | 7 N/25 mm 10 N/25 mm |
| Fogging value reflectometric in accordance with DIN 75201 | 98,3 % |
| Fogging value gravimetric in accordance with DIN 75201 | < 0,2 mg |
| Odour value in accordance with VDA 270 after 24 h storage at room temperature | not bothering |



^{*} Specific test results, statistically not approved.

** Reached temperature in a rising heat test according to the internal test method PM-211 following DIN EN 1943 at 0,5 kg strength, beginning at 30 °C, increasing of temperature every 30 minutes by 10 °C.

DuploCOLL® 50 U

Art. No. 11 00 78

Environmentally friendly transfer tape with dispersion acrylic adhesive

| Technical Data | | | 1 |
|----------------|--|-------------------------|---|
| Shear strength | on steel according to DIN EN 1943, edition 1996, at +23 °C +/- 2°C | 8 N/625 mm ² | |
| Peel strength | on steel according to DIN EN 1939, edition 1996, at +23 °C +/- 2°C | 20 N/25 mm | |

| Application | |
|-------------------------------------|-----------------------|
| Recommended application temperature | 18 °C to 35 °C |
| Application guidelines | www.lohmann-tapes.com |

Storage

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %). The storage stability is one year after delivery.

| Product presentation | | | | | |
|-------------------------|---|------|--|--|--|
| Converted product | Rolls | | | | |
| Width [mm] | 1000 | 1500 | | | |
| Length [m] | 200 | 200 | | | |
| Max. log width: 1500 mm | Other dimensions, die-cuts and sheets on request. | | | | |

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

IMPORTANT NOTE

The physical characteristics contained in this data sheet represent typical or average values. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. Many factors beyond our control and uniquely within buyer's knowledge and control can affect the use and performance of our tape in a particular application. EXCEPT AS EXPRESSIVELY AGREED IN WRITING WE DO NOT TAKE OVER ANY WARRANTY OR LIABILITY FOR THE SUITABILITY OR USABILITY OF OUR TAPES FOR CERTAIN PURPOSES AND APPLICATIONS RESULTING FROM BUYER'S SPECIAL USAGE OF THE TAPES. EXCEPT WHERE PROVIDED BY MANDATORY LEGAL PROVISIONS, WE WILL NOT BE LIABLE FOR ANY DIRECT OR INDIRECT MATERIAL OR IMMATERIAL LOSSES OR DAMAGES ARISING FROM THE USAGE OR APPLICATION OF OUR TAPES. Solely the buyer is responsible for determining the suitability of the specific tape for its use in connection with his method of application. Please consult our Technical Applications Department for specific advice.

Date of issue: October 2016

Lohmann GmbH & Co. KG Irlicher Strasse 55 56567 Neuwied Germany

Phone: + 49 (0) 26 31 34 - 0
Fax: + 49 (0) 26 31 34 - 6661
E-mail: info@lohmann-tapes.com

